

# Specjal Plus

| TECHNICAL DATA   | STANDARD  | SPECJAL PLUS  | SPECJAL PLUS 1.5 MM  |
|--|---|---|--|
| <b>CLASSIFICATION</b>                                      |   |   |  |
| Classification   | EN ISO 10581                                      | Homogeneous single layered vinyl flooring   | Homogeneous single layered vinyl flooring                              |
|  | EN ISO 10874                                      | Commercial: 34 / Industrial: 43   | Commercial: 32 / Industrial: 41  |
| CE certification   | EN 14041  | Yes   | Yes  |
| Wear layer binder content                                  | EN ISO 10581                                      | Type II   | Type II  |
| <b>TECHNICAL CHARACTERISTICS</b>                           |   |   |  |
| Total thickness  | EN ISO 24346                                      | 2.0 mm  | 1.5 mm   |
| Total weight   | EN ISO 23997                                      | 3300 g/m <sup>2</sup>   | 2400 g/m <sup>2</sup>  |
| Wear layer thickness                                       | EN ISO 24340                                      | 2.0 mm  | 1.5 mm   |
| Surface treatment  |   | PUR   | PUR  |
| Form of delivery   | EN ISO 24341 Sheet (rolls)                        | 23 running metres x 200 cm<br>Art. no. 21097 ___ 3 digit colour number                      | 25 running metres x 200 cm<br>Art. no. 21102 ___ 3 digit colour number |
|  | EN ISO 24342 Tiles (box)                          | 61 x 61 cm - 14 tiles/box = 5.21 m <sup>2</sup><br>Art. no. 21098 ___ 3 digit colour number | -  |
| <b>PERFORMANCES FOR CE MARKING REQUIREMENTS (EN 14041)</b> |   |   |  |
| Declaration of Performance                                 | EN 14041  | 0019-0064-DoP-2019-05   | 0019-0064-DoP-2019-05  |
| Reaction to fire   | EN ISO 13501-1<br>EN ISO 9239-1<br>EN ISO 11925-2 | Bfl-s1<br>≥ 8 kW/m <sup>2</sup><br>Pass   | Bfl-s1<br>≥ 8 kW/m <sup>2</sup><br>Pass                                |
| Static electrical discharge                                | EN 1815   | < 2.0 kV  | < 2.0 kV   |
| Thermal resistance   | EN 12667  | Approx. 0.01 m <sup>2</sup> K/W   | Approx. 0.01 m <sup>2</sup> K/W  |
| Slip resistance  | EN 13893  | μ ≥ 0,3   | μ ≥ 0,3  |
| <b>TECHNICAL PERFORMANCES</b>                              |   |   |  |
| Residual indentation                                       | EN ISO 24343-1                                    | Required value: ≤ 0.10 mm<br>Best measured value*: 0.04 mm                                  | Required value: ≤ 0.10 mm<br>Best measured value*: 0.04 mm             |
| Slip resistance  | DIN 51130   | R9  | R9   |
| Castor chair   | ISO 4918  | Suitable  | Suitable   |
| Light fastness   | EN ISO 105-B02                                    | ≥ level 6   | ≥ level 6  |
| Dimensional stability                                      | EN ISO 23999                                      | ≤ 0.40% for rolls<br>≤ 0.25% for tiles  | ≤ 0.40% for rolls<br>-   |
| Flexibility  | ISO 24344   | Pass  | Pass   |
| Chemical resistance  | EN ISO 26987                                      | Good resistance   | Good resistance  |
| Bacteria resistance  | ISO 846 Part C                                    | Does not favour growth  | Does not favour growth   |
| Underfloor heating   |   | Suitable - max. 27°C  | Suitable - max. 27°C   |
| Seam strength  | EN 684  | Average value: ≥ 240 N/50mm<br>Individual values: ≥ 180 N/50mm                              | Average value: ≥ 240 N/50mm<br>Individual values: ≥ 180 N/50mm         |
| <b>ENVIRONMENTAL PERFORMANCES</b>                          |   |   |  |
| Total VOC emissions  | ISO 16000-9                                       | ≤ 10 μg/m <sup>3</sup> (after 28 days)  | ≤ 10 μg/m <sup>3</sup> (after 28 days)                                 |
| <b>COLOURS</b>   |   |   |  |
|  |   | 16  | 16   |

The above information is subject to modification for the benefit of further improvement. (06/19).  
According to the European Regulation N° 305/2011 for CE Marking, the Declarations of Performance are available on our website [www.tarkett.com](http://www.tarkett.com)  
Tarkett's instructions regarding installation, cleaning and maintenance should be observed. Please contact Tarkett at the address shown for these instructions.



| Colour No. | Welding No. | Colour No. | Welding No. | Colour No. | Welding No. | Colour No. | Welding No. |
|------------|-------------|------------|-------------|------------|-------------|------------|-------------|
| 21097 191  | 1287 338    | 21097 196  | 1287 806    | 21097 265  | 1287 377    | 21097 270  | 1291 788    |
| 21097 192  | 1287 374    | 21097 197  | 1287 308    | 21097 267  | 1287 625    | 21097 334  | 1287 041    |
| 21097 193  | 1292 319    | 21097 198  | 1287 211    | 21097 268  | 1287 378    | 21097 335  | 1287 450    |
| 21097 195  | 1287 233    | 21097 199  | 1292 465    | 21097 269  | 1287 182    | 21097 336  | 1287 105    |

## For informations, please contact:

sales-wa@polystyl-asia.com  
(India, Sri Lanka, Maldives, Bangladesh, Bhutan, Nepal, Pakistan)

sales-sea@polystyl-asia.com  
(Singapore, Vietnam, Cambodia, Thailand, Malaysia, Philippines, Indonesia, Myanmar, Brunei)

sales-nea@polystyl-asia.com  
(Japan, South-Korea, Taiwan, Hong Kong, Macau)

[www.polystyl-asia.com](http://www.polystyl-asia.com)

**POLY  
STYL**

HOMOGENEOUS  
COMPACT VINYL

**POLY  
STYL**

# Specjal Plus

HOMOGENEOUS COMPACT VINYL

The Fresh soft  
classics of  
Homogeneous  
solutions

Specjal Plus

phthalate free  
100%



ROLL

TILE

Printed on 100% recycled paper and cardboard - recyclable

Customs tariff: 4820500000

Specjal Plus - 310001 0008 - 06/19

# Specjal Plus

- Soft colours in harmony
- Easy to mix and match
- PUR Surface treatment
- Sheet and tiles in different thickness



LRV: 60%


soft yellow



© 21097 334 NCS S 1515-Y20R  
□ 21098 334

LRV: 40%


soft green



© 21097 335 NCS S 3010-G20Y  
□ 21098 335

LRV: 46%


soft aqua blue



© 21097 267 NCS S 2020-B  
□ 21098 267

LRV: 24%

soft blue




© 21097 336 NCS S 4020-R80B  
□ 21098 336

LRV = Luminous Reflectance Value

LRV: 42%

soft orange



© 21097 265 NCS S 2030-Y40R  
□ 21098 265

LRV: 64%

light sand



© 21097 198 NCS S 1505-Y30R  
□ 21098 198

LRV: 56%


sand



© 21097 199 NCS S 2010-Y30R  
□ 21098 199

LRV: 32%


dark sand



© 21097 268 NCS S 4010-Y30R  
□ 21098 268

LRV: 54%


light beige



© 21097 193 NCS S 2005-Y50R  
□ 21098 193

LRV: 40%


beige



© 21097 195 NCS S 3005-Y50R  
□ 21098 195

LRV: 23%


brown



© 21097 196 NCS S 5010-Y50R  
□ 21098 196

LRV: 13%


dark brown



© 21097 197 NCS S 7005-Y20R  
□ 21098 197

LRV: 65%


white grey



© 21097 191 NCS S 1500-N  
□ 21098 191

LRV: 50%

light grey



© 21097 192 NCS S 2500-N  
□ 21098 192

LRV: 39%

grey



© 21097 269 NCS S 3500-N  
□ 21098 269

LRV: 22%

dark grey



© 21097 270 NCS S 5500-N  
□ 21098 270

